





## UPHOLSTERY FABRIC SPECIFICATION

DESIGN	GO-GO	REPORT No.	A.C.T. 019
CONTENT	27% polyester 24% Australian worsted wool 17% nylon 16% cotton 16% acrylic		
WIDTH	55" (140cm)	DATE	07/30/02
ROLL SIZE	49yds (45m)	WEIGHT	17 oz sq yd (520gsm)
PATTERN REPEAT	Nil	RECOMMENDED CARE CODE	- S

Item	Test Method	Test Results	
 General Contract Upholstery	ASTM 3597 Wyzenbeek modified (#10 cotton duck) Report # AWTA 7-511488-MN	>100,000	
	ASTM 4966 Martindale (21oz weight) Report # DJH 211492	25,000	
	California Bulletin 117 Section E Report # Applied Textiles 97442	Compliance	
	ASTM E 84 (unadhered method) ANSI 2.5, NFPA 255, UBC 42-1, UL 723 Report # Applied Textiles 97442	Flame Spread Index Smoke Developed Index Class 3 or C	100 80
	AATCC 8 Colourfastness to Wet & Dry Crocking Report # AWTA 7-511488-MN	Dry Crocking 4-5 Wet Crocking 4-5	
	AATCC 16E Colourfastness to Light Report # AWTA 7-511488-MN	> 5	
<b>ENVIRONMENTAL INFORMATION SYSTEM</b>	<u>Raw Materials</u>		
	- 60% rapidly renewable content		
	<u>Human Health</u>		
	- Wool and cotton absorbs prevalent indoor air contaminants therefore benefiting indoor air quality		
<u>Disposal</u>			
- Reusable and 40% biodegradable (natural fibre content)			

APPROVED BY:  
Louise Cramp, BSC Textile Technology, Product Manager.



REVISION: R107/01/021101